

## Defoamer BR 1158

### TECHNICAL INFORMATION

**Defoamer for aqueous systems**

**Composition:** Blend of organic modified polysiloxanes emulsified in water

**Appearance:** Liquid

**Colour:** White,turbid

#### Typical Properties:

Active ingredients:	approx.25%
Consistency:	approx. 5000 mPa s
Density at 20°C::	approx. 0.98 g/cm <sup>3</sup>
pH (conc.)::	approx. 7
Solubility in water:	miscible in any ratio

*This information is intended as a guideline only and should not be used to issue specification. Slight deviations do not affect application and capability of the product. For specifications please consult the Certificate of Analysis.*

**Properties/applications:** Defoamer BR 1158 is a polysiloxane emulsion with excellent stability and defoaming persistency. The defoamer is miscible with water in all ratios. Defoamer BR 1158 can be used in pigmented and non-pigmented water based systems. Defoamer BR 1158 is especially designed for the use in water based wood coatings, particularly airless, airmix and HVLP applied coatings and parquet lacquers

#### Main applications:

- Industrial and wood coatings
- Printing inks
- Emulsion manufacturing
- Adhesives

**Recommended levels/use:** Ladder studies are recommended to determine

optimum concentration level. Normal dosage range from 0.05 to 0.5% on finished product. BR 1158 is typically added undiluted during pigment grinding for optimum distribution and de-aeration. For most

● 所有资料，包括配方均是真实的。但是客户必须在自己的试验室或设备上试验来确认，供应商不能做出任何承诺。客户必须遵守当地的专利法规。供货商有权对自己的产品进行改进，其规格有任何改动，恕不提前通知。

## **BOR**

---

efficient use 2/3 of BR 1158 is added to the pigment dispersion and 1/3 is added to the letdown.

**Storage/handling:** BR 1158 is not sensitive to freezing. For better handling it

should be stored between 5°C and 25° C. Frozen product must be defrosted and homogenized by stirring before use. As the product tends to separate slightly it must be stirred before use. The minimum shelf life in closed containers is 9 months from the date of manufacture.

**Packaging:** Totes holding 1000 kg net, drums holding 140 kg net and kegs holding 25 kg net.

● 所有资料，包括配方均是真实的。但是客户必须在自己的试验室或设备上试验来确认，供应商不能做出任何承诺。客户必须遵守当地的专利法规。供货商有权对自己的产品进行改进，其规格有任何改动，恕不提前通知。

---

