

## Dispersant BR 2490

Wetting agent and dispersant for aqueous coatings and pigment concentrates

### Physical and chemical data

Composition:

Solution of a high molecular weight copolymer with pigment affinic groups in water, nonionic

Appearance: liquid  
Colour: brownish, yellow

### Typical Properties:

Active ingredients: approx. 40 %  
Consistency: medium viscosity  
Density at 20 °C: approx. 1.0 g/cm<sup>3</sup>  
Flash point: > 100 °C  
pH (2% in D.I. water) approx. 8

This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product. For specifications please consult the Certificate of Analysis.

### Properties and applications

Dispersant BR 2490 is a VOC-free wetting agent and dispersant for organic and inorganic pigments as well as carbon blacks in aqueous media. It is ideal for the manufacture of flood/float-free aqueous coatings systems (air dry and force dry, 2K-systems) as well as for the manufacture of aqueous resin-free pigment concentrates. BR 2490 stabilizes pigment dispersions and reduces the mill-base viscosity. Gloss, colour strength and hiding power are improved and reflocculation is prevented. BR 2490 allows to achieve very high pigment loading at low dosage in binder free pigment paste formulations.

● 所有资料，包括配方均是真实的。但是客户必须在自己的试验室或设备上试验来确认，供应商不能做出任何承诺。客户必须遵守当地的专利法规。供货商有权对自己的产品进行改进，其规格有任何改动，恕不提前通知。

## Recommended levels and use

Ladder studies are recommended to determine optimum concentration level. Normal dosage ranges from 10 - 50 % BR 2490 in delivery form for organic pigments and carbon blacks, calculated on pigment solids. For dosage recommendations of specific pigments and for determination of dispersant demand please consult our additional technical information and guide formulations.

## Storage and handling

Dispersant 2490 is not sensitive to freezing but for better handling it should be stored between 5 °C and 25 °C. The minimum shelf life in closed containers is 12 months from the date of dispatch.

## Packaging

Totes holding 1000 kg net, drums holding 155 kg net and kegs holding 30 kg net.

We believe all information in this literature to be reliable. No warranties, express or implied are made, any implied warranty of fitness for a particular purpose is expressly disclaimed. We recommend that the prospective user determine the suitability of our materials and recommendations before adopting them on a commercial scale. Patents or other legal rights may not be violated under any given circumstances.

● 所有资料，包括配方均是真实的。但是客户必须在自己的试验室或设备上进行试验来确认，供应商不能做出任何承诺。客户必须遵守当地的专利法规。供货商有权对自己的产品进行改进，其规格有任何改动，恕不提前通知。

---